

PETG-ESD

Technical Data Sheet

PETG-ESD is an antistatic modified material with excellent permanent antistatic effect, surface resistivity of $10^9 \Omega$, easy to print and smooth surface. With balanced strength, stiffness and toughness, it is suitable for areas that require electrostatic protection for precision electronic components, integrated circuits and their packages.

Basic Information

Characteristics	• Good Toughness	• Smooth Print Surface
	• Chip Packaging	• Anti-Dust and Antistatic
	• High Speed Printing	
Applications	• Precision Electronic Components	• Integrated Circuit Parts
	• Chip Packaging	• Other parts requiring
Processing Method	• 3D Printing	• FDM Print

Physical Properties	Testing Method	Data
Density	GB/T 1033	1.22 g/cm ³
Melt Flow Index	GB/T 3682	18.1 (230°C/5kg)

Thermal Properties	Testing Method	Data
Heat Distortion Temperature	GB/T 1634	68 °C (0.45Mpa)
Glass Transition Temperature		N/A
Continuous Service Temperature	IEC 60216	N/A
Maximum (short term) Use Temperature		N/A

Electrical Properties	Testing Method	Data
Insulation Resistance	DIN IEC 60167	N/A
Surface Resistance	DIN IEC 60093	$10^9 \Omega$

Mechanical Properties	Testing Method	Data
Tensile Strength (X-Y)	GB/T 1040	48.11±0.535 Mpa
Tensile Strength (Z)	GB/T 1040	19.34±5.801 MPa
Elongation at Break (X-Y)	GB/T 1040	8.97±1.62 %
Elongation at Break (Z)	GB/T 1040	2.52±0.75 %
Flexural Strength (X-Y)	GB/T 9341	77.7±0.7MPa
Flexural Strength (Z)	GB/T 9341	41.2±3.0 Mpa
Flexural Modulus (X-Y)	GB/T 9341	2162.79±61.09 MPa
Flexural Modulus (Z)	GB/T 9341	1483.12±58.639 Mpa
IZOD Impact Strength (X-Y)	GB/T 1843	4.95 KJ/m ²
IZOD Impact Strength (Z)	GB/T 1843	1.93KJ/m ²

Chemical Properties	Data
Acid and Alkali Resistance	N/A
Grease Resistance	N/A
UV Resistance	Not resistant to light and ageing
Water Repellency	N/A

Recommended Printing Parameters	Data
Drying Preparation	65°C > 8H
Extruder Temperature	
Nozzle Size	0.2,0.4,0.6,0.8mm
Nozzle Temperature	240-260°C
Build Platform Type	PEI
Build Platform Temperature	70°C
Build Platform Preparation	
Fan Speed	40-90%
Printing Speed	< 300mm/s

Printing Tips

1. When slicing, it is recommended to enable the Z-seam alignment and starting point alignment functions, disable the Z-axis lift and exit feature, avoid traversing through the shell during idle movements, optimize the slicing printing path, and appropriately reduce the printing speed in order to achieve optimal print quality.


Test Conditions of Mechanical Properties



Tensile testing specimen GB/T 1040



Flexural testing specimen GB/T 9341



Impact testing specimen GB/T 1043

The performance of the filament is evaluated based on standard samples printed by eSUN, while the actual printing performance is influenced by various factors such as printer type, printing parameters, and print environment.

Printing Test Conditions:

Extruder Temperature	240°C
Build Platform Temperature	70°C
Outer Layer Number	2
Top/Bottom Layer Number	3
Infill Density	100%
Fan Speed	40%
Maximum Volumetric Flow Rate	

*Based on Bambu P1S 0.4 mm nozzle and Orcaslicer 2.1.0 Beta.

Notice

The information provided by or on behalf of eSUN regarding this product, whether in the form of data, recommendations, or otherwise, is supported by thorough research and believed to be reliable in good faith. However, please note that the product is sold "as is". eSUN assumes no liability and does not make any express or implied representations or warranties regarding the merchantability, fitness for a particular purpose, or any other nature of the information or the product it pertains to. This statement does not waive any conditions of sale set forth by the seller.

15AB, Microsoft Ketong Building, No. 55, Gaoxin South Nine Road, Yuehai Street, Nanshan District, Shenzhen, China

Tel: (086)-0755-86581960

Fax: (086)-0755-26031982

Email: bright@brightcn.net

www.esun3d.com